

# Argotec™ 38214

## General Description

**Typical application:** Used in a wide range of outdoor exposed applications.

**Polymer:** Thermoplastic polyurethane, aliphatic polyether

**Extrusion Method:** Blown film

**Key attributes:**

- Non-yellowing
- UV resistant
- Low gel

Typical Property	Test Method	Value
Gauge		2 - 10 mils (50 - 250 microns)
Width		15"-62" (0.38 - 1.57 m)
Length		Up to 1000 non-spliced yards (914.4 m)
Durometer	ASTM D-2240	87A
Tensile strength @ 100% elongation	ASTM D-412	1000 psi (6.9 MPa)
Tensile strength @ 300% elongation		4300 psi (30MPa)
Ultimate tensile strength		7700 psi (53MPa)
Elongation at break		390%

info@argotec.com  
argotec.com

ARG\_TDS\_V01\_20231106

Copyright ©Mativ Holdings, Inc. (2023). All Rights Reserved. ARGOTEC™ is trademarks of Mativ Holdings, Inc. ("Mativ") or an affiliated company of Mativ.

All statements, product characteristics, and performance data contained herein are believed to be reliable based on observation and testing, but no representations, guarantees, or warranties of any kind are made as to accuracy, suitability for particular applications, or the results to be obtained. Nothing contained herein is to be considered to be permission or a recommendation to use any proprietary process or technology without permission of the owner. No warranty of any kind, expressed or implied, is made or intended.