

Argotec™ HP-8000

General Description

Typical application: Glass lamination optical interlayer film

Polymer: Thermoplastic polyurethane, aliphatic polyether

Key attributes:

- Eliminates need for glass surface primer
- Clear, non-yellowing
- Contains additive package for UV resistance

Property		Test Method	Typical Value
Gauge Ranges		N/A	15, 25, 50 mils (380, 635, 1270 microns)
Width Ranges		N/A	Up to 80 Inches (2.03 meters)
Length Ranges		N/A	Up to 500 lin-ft (152.4 meters)
Durometer		ASTM D-2240	75A
Specific gravity		ASTM D-792	1.08
Tensile strength	@100%	ASTM D-638 (Die-IV used with grip separation rate of 20-in./min. on SU 50-mil film)	518 psi (3.57 MPa)
	@200%		744 psi (5.13 MPa)
	@300%		1391 psi (9.60 MPa)
	@Break		5800 psi (40.03 MPa)
Elongation @ break			550%
Tear strength		ASTM D-624	263 pli (42.0 kN/m)
DSC mid point, Tg°C		N/A	-50
TMA peak			194°F (90°C)
TMA range			158-266°F (70-130°C)
Coefficient of thermal expansion			177.97/ppm/oC
Compression set, 22 hrs	@72°F/22°C	ASTM D-395	86
	@158°F/70°C		106
Haze*		ASTM D-1003	< 1.0%
Transmission*			85 - 91%
Yellowness index*		ASTM E-313	< 1
Refractive index*		ASTM D-542	1.501

*Film tested between two pieces of 1/8-in. glass; sample size 4"x4"x50-mil; lamination temp 255°F; time & pressure: 45 seconds @ 100 psi, 45 seconds @ 300 psi

info@argotec.com
argotec.com

ARG_TDS_V02_20240405

Copyright ©Mativ Holdings, Inc. (2024). All Rights Reserved. ARGOTEC™ is trademarks of Mativ Holdings, Inc. ("Mativ") or an affiliated company of Mativ.

All statements, product characteristics, and performance data contained herein are believed to be reliable based on observation and testing, but no representations, guarantees, or warranties of any kind are made as to accuracy, suitability for particular applications, or the results to be obtained. Nothing contained herein is to be considered to be permission or a recommendation to use any proprietary process or technology without permission of the owner. No warranty of any kind, expressed or implied, is made or intended.