

Coretec™ SS-1485

General Description

Typical application: Tubing

Polymer: Thermoplastic polyurethane, aromatic polyester

Packaging: Bulk spools, 100-foot (30.5 m) coils or cut pieces

Key attributes:

- Tough, strong
- Long lasting
- Kink resistant
- Abrasion resistant
- Chemical resistant
- Wide operating temperature range
- Easy processing in assembly operations

Physical Property	Test Method	Value
Inside diameter	N/A	1/16" - 1.0" (1.59 - 25.4 mm)
Outside diameter	N/A	1/8" - 1-1/4" (3.17 - 31.8 mm)
Durometer	ASTM D-2240	Shore 85A (+/- 5)
Specific gravity	ASTM D-792	1.20
Modulus @ 100% strain	ASTM D-638	800 psi (5.51 MPa)
Modulus @ 300% strain		1800 psi (12.41 MPa)
Modulus @ break		7000 psi (48.26 MPa)
Modulus of elasticity up to 10% strain		30 psi (0.21 MPa)
Elongation @ break		400%
Set @ break		30%
Tear strength	D-624 ¹	425 pli (74.38 kN/m)
Max continuous service temperature	N/A	-40°F to 225°F (-4°C to 107°C)
Melt point range	N/A	360°F to 400°F (182°C to 204°C)

¹Die C